

Application Instructions

HEMPADUR MASTIC 45880 / HEMPADUR MASTIC 45881



Low to medium temperatures: 45880: BASE 45889 with CURING AGENT 95880

High temperature: 45881: BASE 45889 with CURING AGENT 95881

For product description refer to product data sheet 45880/ 45881

Scope: These Application Instructions cover surface preparation, application equipment and application details for HEMPADUR MASTIC 45880/45881.

Surface preparation: General:
In order to obtain best performance, abrasive blast cleaning is recommended. However, HEMPADUR MASTIC 45880/45881 has "surface tolerant" properties and offers higher performance than many other coatings when applied to surfaces mechanically cleaned only (salts, oil, grease etc. shall always be removed).

Remove oil and grease with suitable detergent, salt and other contaminants by (high pressure) fresh water cleaning.

NEW STEEL:

When used as intermediate and/or finishing coat, surface preparation according to Product Data Sheet for the preceding primer coat (HEMPADUR primers). When used as a selfpriming coat, surface preparation according to specification.

When applied to GALVOSILS:

HEMPADUR MASTIC 45880/45881 can be applied when the GALVOSIL is cured. Consult APPLICATION INSTRUCTIONS for the relevant GALVOSIL. Remove oil and grease etc. with suitable detergent. Remove salt and other contaminants by high pressure fresh water cleaning. After exposure to high humidity, zinc salts, "white rust", must be removed carefully by high pressure fresh water cleaning, if necessary combined with scrubbing with stiff nylon brushes.

Repair and maintenance:

Spot-repairs:

Clean damaged areas thoroughly by power tool cleaning to minimum St 2 (spot-repairs) or by abrasive blasting to minimum Sa 2, preferably Sa 2½. Improved surface preparation will improve the performance of HEMPADUR MASTIC 45880/45881. As an alternative, water jetting to minimum Wa 2½ (ISO 8501-4:2006)(or according to specification) may be used. A flash-rust degree of maximum M (ISO 8501-4:2006) is acceptable before application. Feather edges to sound and intact areas. Brush off loose material. Touch up to full film thickness.

Compatibility:

HEMPADUR MASTIC 45880/45881 may be used in connection with other generic paint systems than epoxy and polyurethanes.

It is recommended to make a test patch. In any case it is a must that the old paint system is tightly adhering and is properly prepared before the touch-up is performed.

Full coating:

Compatibility with old system:

In general full compatibility can be expected with old epoxy systems. A test patch should always be performed before full coating is decided. If the old epoxy is not weathered/chalked or if it is topcoated with polyurethane, it is recommended to roughen the surface before overcoating. Furthermore, very thorough cleaning is a must. Any dirt, chalked surface material, oil and grease should be removed with suitable detergent followed by high pressure fresh water hosing of the entire surface.

Removal of old system:

Full coating after complete mechanical removal of an old paint system is possible too. Yet, it must be considered that mechanical cleaning by disc grinding or by rotating wire brushing may produce a very smooth surface which reduce the adhesive forces of the primer coat

Note: Another risk is remains of a hard black rust scale being cleaned to an apparent brightness without showing any adhesive defects.

Yet, the exposure to open air during cleaning may have started a further oxidation of the hard black rust making it mechanically weak and of poor adhesion to the underlying steel surface. Later, during service, the scale plus overlying paint material may flake off.

Application Instructions

HEMPADUR MASTIC 45880 / HEMPADUR MASTIC 45881

Low to medium temperatures: 45880: BASE 45889 with CURING AGENT 95880

High temperature: 45881: BASE 45889 with CURING AGENT 95881



When used for immersion service, repair:

Remove oil and grease, etc. with suitable detergent. Remove salt and other contaminants by (high pressure) fresh water cleaning. Clean damaged areas thoroughly by power tool cleaning to St 3 (minor areas) or by abrasive blasting to min. Sa 2, preferably Sa 2½. Improved surface preparation will improve the performance of HEMPADUR MASTIC 45880/45881. As an alternative to dry cleaning, water jetting to minimum Wa 2½ (ISO 8501-4:2006), may be used. A flash rust degree of M, preferably L (ISO 8501-4:2006) is acceptable before application. Feather edges to sound intact areas. Dust off residues. Touch up to full film thickness

Note: On old steel surfaces having been exposed to salty water, excessive amounts of salt residues in pittings may call for high pressure water jetting, wet abrasive blasting, alternatively dry abrasive blasting, high pressure fresh water hosing, drying, and finally, dry abrasive blasting again.

Application equipment: HEMPADUR MASTIC 45880/45881 being a high solids and a relatively high viscosity material, may require special measures to be taken at application.

Recommended airless spray equipment:

Pump ratio:	min. 45:1
Pump output:	12 litres/minute (theoretical)
Input pressure:	min. 6 bar/90 psi
Spray hoses:	max. 100 metres/300 feet, ½" internal diameter max. 30 metres/100 feet, 3/8" internal diameter max. 6 metres/20 feet, 1/4" internal diameter
Regular surfaces:	
Nozzle size:	.021" through .023"
Fan angle:	60°
Complicated surfaces (and touch up):	
Nozzle size:	.017" through .021"
Fan angle:	40°
Airless spray data are indicative and subject to adjustment.	

After finishing the application, clean the equipment immediately with THINNER 08450 or HEMPEL'S TOOL CLEANER 99610.

Note: Increasing hose diameter may increase paint flow, thereby improving the spray fan. If longer hoses are necessary it may be necessary to raise the pump ratio to 60:1, maintaining the high output capacity of the pump.

Alternatively up to approx. 5% THINNER 08450 may be added, but thinning must be done with care as the anti-sagging properties are drastically reduced by overthinning.

Induction time: Should the paint temperature as an exception be 15°C/59°F or below, it is an advantage to allow the two components to prereact before application. This is especially relevant in the case of substrate temperatures also being below 15°C/59°F.

In case of a paint or substrate temperature at 15°C/59°F, an induction time of 15 minutes is recommended. In case of a paint or substrate temperature at 10°C/50°F, an induction time of 25 minutes is recommended. In order to obtain proper application properties, the paint temperature should preferably never be below 10°C/50°F. Yet for substrate temperatures below 10°C/50°F an induction time of 30 minutes is recommended.

Spray application:

Film-build/continuity:

With this paint material applied in one/few coat(s) it is of special importance that a continuous, pinhole-free paint film is obtained at application of each coat. An application technique which will ensure good film formation on **all** surfaces must be adopted. It is very important to use nozzles of the correct size, not too big, and to have a proper, uniform distance of the spray gun to the surface, 30-50 cm should be aimed at. Furthermore, great care must be taken to cover edges, openings, rear sides of stiffeners etc. Thus, on these areas application of a stripe coat will therefore be good painting practice. To obtain good and steady atomizing, the viscosity of the paint must be suitable and the spray equipment must be sufficient in output pressure and capacity. At high working temperatures, use of extra thinner may be necessary to avoid dust-spray.

Application Instructions

HEMPADUR MASTIC 45880 / HEMPADUR MASTIC 45881

Low to medium temperatures: 45880: BASE 45889 with CURING AGENT 95880

High temperature: 45881: BASE 45889 with CURING AGENT 95881



The paint layer must be applied homogeneously and as close to the specification as possible. Avoid exaggerated film thickness due to the risk of sagging, cracks and solvent retention. The paint consumption must be controlled.

The finished coating must appear as a homogeneous film with a smooth surface and irregularities such as dust, dry spray, abrasives, should be remedied.

Brush and roller application:

At application with hand tools, brush, but especially by roller the natural tendency to a more uneven paint film obtained by these methods, is to be counteracted by more coats applied. If at all possible each coat is to be applied across the preceding one - in general follow good painting practise.

On **poorly prepared surfaces** it is always recommended to apply the first coat by brush. Extra thinning will facilitate the penetration of the paint material, but will also require an extra layer to be applied.

Wet/dry film thickness: HEMPADUR MASTIC 45880/45881 is normally specified in 125-200 micron/5-8 mils. Depending on ambient conditions, usually maximum 5% thinning with THINNER 08450 is relevant, however, increasing at high temperatures to ensure proper film formation and avoid dust spray. May be specified down to 100 micron/4 mils. To obtain optimum film formation in film thicknesses lower than 125 micron/5 mils dry film thickness additional thinning with 5-10% THINNER 08450 is recommended.

Pot life: When measured under standard conditions the pot life is 1 hour at 20°C/68°F for HEMPADUR MASTIC 45880 respectively 1½ hours at 30°C/86°F for HEMPADUR MASTIC 45881. However, for a 20 litres/5 US gallons mix, and used under warm climate conditions, the heat developed by the chemical reaction between BASE and CURING AGENT may make the corresponding practical pot life shorter.

Therefore: At high temperatures, use the paint immediately after mixing irrespective of equipment

Physical data versus temperature (optional):

Drying time and overcoating interval vary with film thickness, temperature and later exposure conditions.

HEMPADUR MASTIC 45880 in a dry film thickness of 125 micron/5 mils:

Surface temperature:	-5°C/23°F	0°C/32°F	10°C/50°F	20°C/68°F	30°C/86°F	40°C/104°F
Drying time	3 days	36 hours	12 hours	4 hours	3 hours	2 hours
Curing time	2.5 months	1 month	14 days	7 days	5 days	3 days

Surface temperature:	Environment	-5°C/23°F		0°C/32°F		10°C/50°F		20°C/68°F		30°C/86°F		40°C/104°F	
		Min	Max	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max
HEMPADUR	Medium	3.5 d	Ext.	54 h	Ext.	18 h	Ext.	6 h	Ext.	5 h	Ext.	3 h	Ext.
	Severe	7 d	Ext.	3.5 d	Ext.	30 h	Ext.	10 h	Ext.	8 h	Ext.	6 h	Ext.
	Immersion	8.5 d	90 d	4.5 d	90 d	36 h	90 d	12 h	30 d	9 h	23 d	7 h	16 d
HEMPATHANE	Medium	3.5 d	Ext.	54 h	Ext.	18 h	Ext.	6 h	Ext.	5 h	Ext.	3 h	Ext.
	Severe	7 d	52 d	3.5 d	27 d	30 h	9 d	10 h	3 d	8 h	54 h	6 h	40 h

Notes:

- Avoid sudden drops in (substrate) temperatures during drying/initial curing. It is especially important that the substrate temperature does not drop significantly before application of the acrylic or polyurethane finish and that proper ventilation is maintained.
- In case of low temperatures, it is recommended that HEMPADUR MASTIC 45880 has been given a proper induction time before application. Under such conditions, consider paint temperature equal to substrate temperature and follow the rules given on under "Induction time".
- Depending on actual local conditions, extended maximum overcoating intervals may apply. Please contact Hempel for further advice.

HEMPADUR MASTIC 45881 in a dry film thickness of 125 micron/5 mils:

Surface temperature:	20°C/68°F	30°C/86°F	40°C/104°F
Drying time	4 hours	3 hours	2 hours
Curing time	7 days	5 days	3 days

Application Instructions

HEMPADUR MASTIC 45880 / HEMPADUR MASTIC 45881

Low to medium temperatures: 45880: BASE 45889 with CURING AGENT 95880

High temperature: 45881: BASE 45889 with CURING AGENT 95881



Surface temperature:		20°C/68°F		30°C/86°F		40°C/104°F	
Overcoat with Quality type:	Environment	Min	Max	Min	Max	Min	Max
HEMPADUR	Medium	7 h	Ext.	6 h	Ext.	4 h	Ext.
	Severe	10 h	Ext.	8 h	Ext.	6 h	Ext.
	Immersion	12 h	30 d	10 h	23 d	7 h	15 d
HEMPATHANE	Medium	7 h	Ext.	6 h	Ext.	4 h	Ext.
	Severe	10 h	10 d	8 h	7.5 d	6 h	5 d

Notes:

- Avoid sudden drops in (substrate) temperatures during drying/initial curing. It is especially important that the substrate temperature does not drop significantly before application of the acrylic or polyurethane finish and that proper ventilation is maintained.
- Depending on actual local conditions, extended maximum overcoating intervals may apply. Please contact Hempel for further advice.

Notes on extended overcoating Intervals with HEMPADUR and HEMPATHANE qualities

Extended overcoating intervals can be utilised when the following is strictly observed:

The surface shall be thoroughly cleaned from all sorts of contaminants including invisible deposits of water soluble salts, oil, grease and similar harmful chemical substances.

Surfaces having any degraded layer from exposure to UV radiation, heat etc. must have this layer removed by mechanical cleaning methods like, water jetting, abrading or sweep blasting.

The existing coating system must in all respects be sound and applied according to Product Data Sheets, Application Instructions and Specification,

It should be recognised that the optimal intercoat adhesion is best ensured by observing the interval between the stated minimum and "Cured Time". Utilising extended overcoating intervals it should further be understood that by chemical nature the intercoat adhesion between HEMPADUR qualities are better than between HEMPADUR and HEMPATHANE qualities. To determine whether the quality of the surface cleaning is adequate, a test patch may be relevant. However, such a test is not the final proof of long-term durability, but if the result is doubtful, repeated cleaning will be relevant. A more safe solution could be to refresh the surface with a new thin (diluted) coat of HEMPADUR MASTIC 45880/45881.

Safety:

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult Hempel Material Safety Data Sheets and follow all local or national safety regulations. Avoid inhalation, avoid contact with skin and eyes, and do not swallow. Take precautions against possible risks of fire or explosions as well as protection of the environment. Apply only in well ventilated areas.

Issued by:

HEMPEL A/S – 4588012170/4588112170

These Application Instructions supersede those previously issued.

For explanations, definitions and scope see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User. The Products are supplied and all technical assistance is given subject to Hempel's general conditions of sales, delivery and service, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said general conditions for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.